

# ITU-T

TELECOMMUNICATION  
STANDARDIZATION SECTOR  
OF ITU

# G.651.1

(07/2007)

SERIES G: TRANSMISSION SYSTEMS AND MEDIA,  
DIGITAL SYSTEMS AND NETWORKS

Transmission media and optical systems characteristics –  
Optical fibre cables

---

**Characteristics of a 50/125  $\mu\text{m}$  multimode  
graded index optical fibre cable for the optical  
access network**

ITU-T Recommendation G.651.1

ITU-T G-SERIES RECOMMENDATIONS  
TRANSMISSION SYSTEMS AND MEDIA, DIGITAL SYSTEMS AND NETWORKS

INTERNATIONAL TELEPHONE CONNECTIONS AND CIRCUITS	G.100–G.199
GENERAL CHARACTERISTICS COMMON TO ALL ANALOGUE CARRIER-TRANSMISSION SYSTEMS	G.200–G.299
INDIVIDUAL CHARACTERISTICS OF INTERNATIONAL CARRIER TELEPHONE SYSTEMS ON METALLIC LINES	G.300–G.399
GENERAL CHARACTERISTICS OF INTERNATIONAL CARRIER TELEPHONE SYSTEMS ON RADIO-RELAY OR SATELLITE LINKS AND INTERCONNECTION WITH METALLIC LINES	G.400–G.449
COORDINATION OF RADIOTELEPHONY AND LINE TELEPHONY	G.450–G.499
TRANSMISSION MEDIA AND OPTICAL SYSTEMS CHARACTERISTICS	G.600–G.699
General	G.600–G.609
Symmetric cable pairs	G.610–G.619
Land coaxial cable pairs	G.620–G.629
Submarine cables	G.630–G.639
Free space optical systems	G.640–G.649
<b>Optical fibre cables</b>	<b>G.650–G.659</b>
Characteristics of optical components and subsystems	G.660–G.679
Characteristics of optical systems	G.680–G.699
DIGITAL TERMINAL EQUIPMENTS	G.700–G.799
DIGITAL NETWORKS	G.800–G.899
DIGITAL SECTIONS AND DIGITAL LINE SYSTEM	G.900–G.999
QUALITY OF SERVICE AND PERFORMANCE – GENERIC AND USER-RELATED ASPECTS	G.1000–G.1999
TRANSMISSION MEDIA CHARACTERISTICS	G.6000–G.6999
DATA OVER TRANSPORT – GENERIC ASPECTS	G.7000–G.7999
PACKET OVER TRANSPORT ASPECTS	G.8000–G.8999
ACCESS NETWORKS	G.9000–G.9999

*For further details, please refer to the list of ITU-T Recommendations.*

## **ITU-T Recommendation G.651.1**

### **Characteristics of a 50/125 $\mu\text{m}$ multimode graded index optical fibre cable for the optical access network**

#### **Summary**

ITU-T Recommendation G.651.1 recommends a quartz multimode fibre to be used for the access network in specific environments. These environments are multi-tenant building sub-networks in which broadband services have to be delivered to individual apartments. The recommended multimode fibre supports the cost-effective use of 1 Gbit/s Ethernet systems over link lengths up to 550 m, usually based upon the use of 850 nm transceivers.

The recommended fibre type is an improved version of the well-known 50/125  $\mu\text{m}$  multimode graded-index fibre as recommended in ITU-T Recommendation G.651. Its cost effective use is very common in datacom systems applied in enterprise buildings throughout the world for quite a number of years.

#### **Source**

ITU-T Recommendation G.651.1 was approved on 29 July 2007 by ITU-T Study Group 15 (2005-2008) under the ITU-T Recommendation A.8 procedure.

## FOREWORD

The International Telecommunication Union (ITU) is the United Nations specialized agency in the field of telecommunications. The ITU Telecommunication Standardization Sector (ITU-T) is a permanent organ of ITU. ITU-T is responsible for studying technical, operating and tariff questions and issuing Recommendations on them with a view to standardizing telecommunications on a worldwide basis.

The World Telecommunication Standardization Assembly (WTSA), which meets every four years, establishes the topics for study by the ITU-T study groups which, in turn, produce Recommendations on these topics.

The approval of ITU-T Recommendations is covered by the procedure laid down in WTSA Resolution 1.

In some areas of information technology which fall within ITU-T's purview, the necessary standards are prepared on a collaborative basis with ISO and IEC.

## NOTE

In this Recommendation, the expression "Administration" is used for conciseness to indicate both a telecommunication administration and a recognized operating agency.

Compliance with this Recommendation is voluntary. However, the Recommendation may contain certain mandatory provisions (to ensure e.g. interoperability or applicability) and compliance with the Recommendation is achieved when all of these mandatory provisions are met. The words "shall" or some other obligatory language such as "must" and the negative equivalents are used to express requirements. The use of such words does not suggest that compliance with the Recommendation is required of any party.

## INTELLECTUAL PROPERTY RIGHTS

ITU draws attention to the possibility that the practice or implementation of this Recommendation may involve the use of a claimed Intellectual Property Right. ITU takes no position concerning the evidence, validity or applicability of claimed Intellectual Property Rights, whether asserted by ITU members or others outside of the Recommendation development process.

As of the date of approval of this Recommendation, ITU had not received notice of intellectual property, protected by patents, which may be required to implement this Recommendation. However, implementers are cautioned that this may not represent the latest information and are therefore strongly urged to consult the TSB patent database at <http://www.itu.int/ITU-T/ipr/>.

© ITU 2008

All rights reserved. No part of this publication may be reproduced, by any means whatsoever, without the prior written permission of ITU.

## CONTENTS

	<b>Page</b>
1 Scope .....	1
2 References.....	1
3 Terms and definitions .....	2
4 Abbreviations and acronyms .....	2
5 Fibre attributes .....	2
5.1 Cladding diameter .....	3
5.2 Core diameter .....	3
5.3 Core concentricity error.....	3
5.4 Non-circularity .....	3
5.5 Numerical aperture .....	3
5.6 Macrobending loss.....	3
5.7 Material properties of the fibre.....	4
5.8 Refractive index profile.....	4
5.9 Modal bandwidth.....	4
5.10 Chromatic dispersion coefficient.....	4
6 Cable attributes .....	5
6.1 Attenuation coefficient .....	5
6.2 Modal bandwidth.....	5
7 Tables of recommended values .....	5
Bibliography.....	7

## **Introduction**

Worldwide, various technologies for broadband access networks are advancing rapidly to provide the high capacity needed for the increasing customer demands with respect to new services. Apart from the technologies, also the network structures and customer densities vary considerably. A specific segment, which is in the main scope of this Recommendation, is the network in a multi-tenant building. Quite a large percentage of all customers in the world are living in these buildings. Due to the high connection density and the short distribution cable lengths, cost-effective high capacity optical networks can be designed and installed by making use of 50/125  $\mu\text{m}$  graded-index multimode fibres. The effective use of this network type has been shown by its extended and experienced use for datacom systems in enterprise buildings with system bit rates ranging from 10 Mbit/s up to 10 Gbit/s. This use is supported by a large series of IEEE system standards and IEC fibre and cable standards which are used as the main references in this Recommendation.

# ITU-T Recommendation G.651.1

## Characteristics of a 50/125 $\mu\text{m}$ multimode graded index optical fibre cable for the optical access network

### 1 Scope

This Recommendation describes a 50/125  $\mu\text{m}$  graded-index multimode optical fibre cable which is suitable to be used in the 850 nm or 1300 nm region, or alternatively may be used in both wavelength regions simultaneously.

The geometrical, optical, transmission and mechanical parameters are described below in two categories of attributes:

- fibre attributes are those attributes that are retained throughout cabling and installation;
- cable attributes that are recommended for cables as they are delivered.

This Recommendation, and the different performance categories found in Table 1, is intended to support the following related system Recommendations and standards:

- [b-IEEE 802.3].

The characteristics of this fibre, including the definitions of the relevant parameters, their test methods and relevant values, will be refined as studies and experience progress.

### 2 References

The following ITU-T Recommendations and other references contain provisions which, through reference in this text, constitute provisions of this Recommendation. At the time of publication, the editions indicated were valid. All Recommendations and other references are subject to revision; users of this Recommendation are therefore encouraged to investigate the possibility of applying the most recent edition of the Recommendations and other references listed below. A list of the currently valid ITU-T Recommendations is regularly published. The reference to a document within this Recommendation does not give it, as a stand-alone document, the status of a Recommendation.

- [IEC 60793-1-1] IEC 60793-1-1 (2002), *Optical fibres – Part 1-1: Measurement methods and test procedures – General and guidance.*
- [IEC 60793-1-20] IEC 60793-1-20 (2001), *Optical fibres – Part 1-20: Measurement methods and test procedures – Fibre geometry.*
- [IEC 60793-1-30] IEC 60793-1-30 (2001), *Optical fibres – Part 1-30: Measurement methods and test procedures – Fibre proof test.*
- [IEC 60793-1-40] IEC 60793-1-40 (2001), *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation.*
- [IEC 60793-1-41] IEC 60793-1-41 (2003), *Optical fibres – Part 1-41: Measurement methods and test procedures – Bandwidth.*
- [IEC 60793-1-42] IEC 60793-1-42 (2007), *Optical fibres – Part 1-42: Measurement methods and test procedures – Chromatic dispersion.*
- [IEC 60793-1-43] IEC 60793-1-43 (2001), *Optical fibres – Part 1-43: Measurement methods and test procedures – Numerical aperture.*
- [IEC 60793-1-47] IEC 60793-1-47 (2006), *Optical fibres – Part 1-47: Measurement methods and test procedures – Macrobending loss.*

- [IEC 60793-1-49] IEC 60793-1-49 (2006), *Optical fibres – Part 1-49: Measurement methods and test procedures – Differential mode delay.*
- [IEC 60793-2] IEC 60793-2 (2003), *Optical fibres – Part 2: Product specifications – General.*
- [IEC 60793-2-10] IEC 60793-2-10 (2007), *Optical fibres – Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres.*
- [IEC 60794-2] IEC 60794-2 (2002), *Optical fibre cables – Part 2: Indoor cables – Sectional specification.*
- [IEC 60794-2-11] IEC 60794-2-11 (2002), *Optical fibre cables – Part 2-11: Indoor cables – Detailed specification for simplex and duplex cables for use in premises cabling.*
- [IEC 60794-2-21] IEC 60794-2-21 (2005), *Optical fibre cables – Part 2-21: Indoor cables – Detailed specification for multi-fibre optical distribution cables for use in premises cabling.*
- [IEC 60794-2-31] IEC 60794-2-31 (2005), *Optical fibre cables – Part 2-31: Indoor cables – Detailed specification for optical fibre ribbon cables for use in premises cabling.*
- [IEC 60794-3-12] IEC 60794-3-12 (2005), *Optical fibre cables – Part 3-12: Outdoor cables – Detailed specification for duct and directly buried optical telecommunication cables for use in premises cabling.*
- [IEC 61280-4-1] IEC 61280-4-1 (2003), *Fibre-optic communication subsystem test procedures – Part 4-1: Cable plant and links – Multimode fibre-optic cable plant attenuation measurement.*

### **3 Terms and definitions**

For the purposes of this Recommendation, the definitions and the guidelines to be followed in the measurement to verify the various characteristics are given in the IEC standards series IEC 60793, IEC 60794 and IEC 61280-4-1. Values shall be rounded to the number of digits given in Table 1 before conformance is evaluated.

### **4 Abbreviations and acronyms**

This Recommendation uses the following abbreviation:

NA Numerical Aperture

### **5 Fibre attributes**

The characteristics of the fibre providing a minimum essential design framework for fibre manufacture, system design and use are recommended in this clause and in clause 7. Ranges or limits on values are presented in Table 1. In this clause those attributes have been listed only where additional information is helpful.

The recommended characteristics will not be significantly affected by cable manufacture or installation and therefore apply equally to individual fibres, fibres incorporated into a cable wound on a drum, and fibres in an installed cable.



## **5.1 Cladding diameter**

The recommended nominal value of the cladding diameter is 125 µm. A tolerance is also specified and shall not exceed the value in clause 7. The cladding diameter deviation from nominal shall not exceed the specified tolerance. For measuring the value of this attribute, reference is made to [IEC 60793-1-20].

## **5.2 Core diameter**

The recommended nominal value of the core diameter is 50 µm. A tolerance is also specified and shall not exceed the value in clause 7. The core diameter deviation from nominal shall not exceed the specified tolerance. For measuring the value of this attribute, reference is made to [IEC 60793-1-20].

## **5.3 Core concentricity error**

The core concentricity error shall not exceed the value specified in clause 7. For measuring the value of this attribute, reference is made to [IEC 60793-1-20].

## **5.4 Non-circularity**

### **5.4.1 Cladding non-circularity**

The cladding non-circularity shall not exceed the value found in clause 7. For measuring the value of this attribute, reference is made to [IEC 60793-1-20].

### **5.4.2 Core non-circularity**

The core non-circularity shall not exceed the value found in clause 7. For measuring the value of this attribute, reference is made to [IEC 60793-1-20].

## **5.5 Numerical aperture**

The numerical aperture (NA) is the sine of the vertex half-angle of the largest cone of rays that can enter or leave the core of an optical fibre, multiplied by the refractive index of the medium in which the vertex of the cone is located. All values measured at 850 nm. The value of the numerical aperture is about 5% lower than the value of the maximum theoretical numerical aperture ( $NA_{tmax}$ ) which is derived from a refractive index measurements trace of the core and cladding.

$$NA_{tmax} = \left( n_1^2 - n_2^2 \right)^{1/2}$$

in which  $n_1$  is the maximum refractive index of the core and  $n_2$  is the refractive index of the innermost homogeneous cladding. For measuring the value of this attribute, reference is made to [IEC 60793-1-43].

## **5.6 Macrobending loss**

Macrobending loss varies with bend radius and number of turns about a mandrel with a specified radius but is rather independent of the measuring wavelength. Therefore, testing at one of the wavelengths specified in clause 7 may be sufficient to ensure compliance with this Recommendation.

When testing multiple macrobends, the mode distribution encountered at a specific macrobend may depend on how many macrobends precede it. For example, the first bend might influence the launch condition at the second bend, and the second bend might influence the launch condition at the third bend, etc. Consequently, the macrobending-added loss at a given bend might be different than the macrobending-added loss at another bend. In particular, the first bend may have the largest influence on following bends. Consequently, the macrobending-added loss produced by multiple

bends should not be expressed in the units of "dB/bend" by dividing the total added loss by the number of bends, but in dB for the specified number of bends. For measuring the value of this attribute, reference is made to [IEC 60793-1-47] and [IEC 61280-4-1].

The macrobending-added loss for the multimode fibre within the scope of this Recommendation is fully determined by its NA value (see Table 1) and the launching conditions at the position in the cable network where a bend is present.

NOTE – A qualification test may be sufficient to ensure that this requirement is being met.

## **5.7 Material properties of the fibre**

### **5.7.1 Fibre materials**

The substances of which the fibres are made should be indicated.

NOTE – Care may be needed in fusion splicing fibres of different substances. Provisional results indicate that adequate splice loss and strength can be achieved when splicing different high-silica fibres.

### **5.7.2 Protective materials**

The physical and chemical properties of the material used for the fibre primary coating and the best way of removing it (if necessary) should be indicated. In the case of single jacketed fibre, similar indications shall be given.

## **5.8 Refractive index profile**

The refractive index profile of the fibre does not generally need to be known.

## **5.9 Modal bandwidth**

The modal bandwidth is specified with a minimum value at one or more wavelengths in both the 850 nm and 1300 nm regions. The optical fibre modal bandwidth shall not be lower than the values recommended in clause 7.

By convention, the modal bandwidth is linearly normalized to 1 km. For measuring the value of this attribute, reference is made to [IEC 60793-1-41].

## **5.10 Chromatic dispersion coefficient**

The chromatic dispersion coefficient,  $D(\lambda)$ , is specified by putting limits on the parameters of a chromatic dispersion curve that is a function of wavelength in the 1300 nm region. The chromatic dispersion coefficient limit for any wavelength,  $\lambda$ , is calculated with the minimum zero-dispersion wavelength,  $\lambda_{0min}$ , the maximum zero-dispersion wavelength,  $\lambda_{0max}$ , and the maximum zero-dispersion slope coefficient,  $S_{0max}$ , according to:

$$\frac{\lambda S_{0max}}{4} \left[ 1 - \left( \frac{\lambda_{0max}}{\lambda} \right)^4 \right] \leq D(\lambda) \leq \frac{\lambda S_{0max}}{4} \left[ 1 - \left( \frac{\lambda_{0min}}{\lambda} \right)^4 \right]$$

The values of  $\lambda_{0min}$ ,  $\lambda_{0max}$  and  $S_{0max}$  shall be within the limits indicated in Table 1. For measuring the value of this attribute, reference is made to [IEC 60793-1-42].

NOTE 1 – The worst-case chromatic dispersion coefficient at 850 nm as derived from the recommended values in clause 7 is  $-104 \text{ ps/nm} \cdot \text{km}$  (e.g.,  $S_0 = 0.09375 \text{ ps/nm}^2 \cdot \text{km}$  at  $\lambda_0 = 1340 \text{ nm}$  or  $S_0 = 0.10125 \text{ ps/nm}^2 \cdot \text{km}$  at  $\lambda_0 = 1320 \text{ nm}$ ).

NOTE 2 – Specification compliance of chromatic dispersion can be assured by compliance to the numerical aperture specification.

## **6 Cable attributes**

Since the geometrical and optical characteristics of fibres given in clause 5 are barely affected by the cabling process, this clause gives recommendations mainly relevant to transmission characteristics of cabled fibres.

Environmental and test conditions are paramount and are described in the guidelines for test methods.

### **6.1 Attenuation coefficient**

The attenuation coefficient is specified with a maximum value at one or more wavelengths in both the 850 nm and 1300 nm regions. The optical fibre cable attenuation coefficient values shall not exceed the values recommended in clause 7. For measuring the value of this attribute, reference is made to [IEC 60793-1-40].

### **6.2 Modal bandwidth**

The cable requirement for modal bandwidth is that the cable shall include fibre that complies with the fibre modal bandwidth-length product as recommended in clause 7.

## **7 Tables of recommended values**

Table 1 summarizes the recommended values for the 50/125  $\mu\text{m}$  graded-index multimode fibres that satisfy the objectives of this Recommendation. They support the application in Ethernet-based systems with transmission speeds ranging up to 1 Gbit/s, either in the 850 nm or in the 1300 nm wavelength window. For the 1 Gbit/s systems, the link length is 550 m both at 850 nm (1000BASE-SX) and at 1300 nm (1000BASE-LX).

The modal bandwidth-length product requirements as stated in Table 1 have been coded as "OM2" in [b-ISO/IEC 11801] and have also been normatively defined in the optical fibre cable standards listed in clause 2. The use of "OM-3" grade multimode fibre, supporting 10 Gbit/s transmission at 850 nm (10GBASE-SX), satisfies the requirements of this Recommendation also because it has higher bandwidth.

Longer link lengths up to 1000 or 2000 m at either one of the two or both wavelength regions can be supported if the customer and the manufacturer agree on improved attribute values, modal bandwidth in particular.

**Table 1 – Attributes**

<b>Fibre attributes</b>		
<b>Attribute</b>	<b>Detail</b>	<b>Value</b>
Cladding diameter	Nominal	125 $\mu\text{m}$
	Tolerance	$\pm 2 \mu\text{m}$
Core diameter	Nominal	50 $\mu\text{m}$
	Tolerance	$\pm 3 \mu\text{m}$
Core-cladding concentricity error	Maximum	3 $\mu\text{m}$
Core non-circularity	Maximum	6%
Cladding non-circularity	Maximum	2%
Numerical aperture	Nominal	0.20
	Tolerance	$\pm 0.015$
Macrobend loss  (Notes 1 and 2)	Radius	15 mm
	Number of turns	2
	Maximum at 850 nm	1 dB
	Maximum at 1300 nm	1 dB
Proof stress	Minimum	0.69 GPa
Modal bandwidth-length product for overfilled launch	Minimum at 850 nm	500 MHz · km
	Minimum at 1300 nm	500 MHz · km
Chromatic dispersion coefficient  (Note 3)	$\lambda_{0\text{min}}$	1295 nm
	$\lambda_{0\text{max}}$	1340 nm
	$S_{0\text{max}}$ for $1295 \leq \lambda_0 \leq 1310 \text{ nm}$	$\leq 0.105$ $\text{ps/nm}^2 \times \text{km}$
	$S_{0\text{max}}$ for $1310 \leq \lambda_0 \leq 1340 \text{ nm}$	$\leq 375 \times (1590 - \lambda_0) \times 10^{-6} \text{ps/nm}^2 \cdot \text{km}$
<b>Cable attributes</b>		
<b>Attribute</b>	<b>Detail</b>	<b>Value</b>
Attenuation coefficient	Maximum at 850 nm	3.5 dB/km
	Maximum at 1300 nm	1.0 dB/km
<p>NOTE 1 – In case of use of the multimode fibre outside the scope of this Recommendation, other macrobending loss values may be valid as specified in [IEC 60793-2-10].</p> <p>NOTE 2 – For testing the macrobending loss value, the launching conditions as specified for the attenuation measurement in [IEC 61280-4-1] shall be used.</p> <p>NOTE 3 – The worst-case chromatic dispersion coefficient at 850 nm (e.g., <math>S_0 = 0.09375 \text{ps/nm}^2 \cdot \text{km}</math> at <math>\lambda_0 = 1340 \text{ nm}</math> or <math>S_0 = 0.10125 \text{ps/nm}^2 \cdot \text{km}</math> at <math>\lambda_0 = 1320 \text{ nm}</math>) is <math>-104 \text{ps/nm} \cdot \text{km}</math>.</p>		

## Bibliography

- [b-ITU-T G.983.x] ITU-T G.983.x series of Recommendations (2001-2005), *Broadband optical access systems based on Passive Optical Networks (PON)*.
- [b-ITU-T G.984.x] ITU-T G.984.x series of Recommendations (2003-2007), *Gigabit-capable Passive Optical Networks (G-PON)*.
- [b-ITU-T L.67] ITU-T Recommendation L.67 (2006), *Small count optical fibre cables for indoor applications*.
- [b-ITU-T ANT] ITU-T SG 15 WP 1; *ANT standards overview*.  
[www.itu.int/itu-t/studygroups/com15/ant/index.html](http://www.itu.int/itu-t/studygroups/com15/ant/index.html)
- [b-IEC 62048] IEC 62048 (2002), *Optical fibres – Reliability – Power law theory*.
- [b-IEEE 802.3] IEEE std. 802.3 (2005), *Part 3: Carrier sense multiple access with collision detection (CSMA/CD) access method and physical layer specifications*.
- [b-ISO/IEC 11801] ISO/IEC 11801:2002, *Information technology – Generic cabling for customer premises*.



## SERIES OF ITU-T RECOMMENDATIONS

Series A	Organization of the work of ITU-T
Series D	General tariff principles
Series E	Overall network operation, telephone service, service operation and human factors
Series F	Non-telephone telecommunication services
<b>Series G</b>	<b>Transmission systems and media, digital systems and networks</b>
Series H	Audiovisual and multimedia systems
Series I	Integrated services digital network
Series J	Cable networks and transmission of television, sound programme and other multimedia signals
Series K	Protection against interference
Series L	Construction, installation and protection of cables and other elements of outside plant
Series M	Telecommunication management, including TMN and network maintenance
Series N	Maintenance: international sound programme and television transmission circuits
Series O	Specifications of measuring equipment
Series P	Telephone transmission quality, telephone installations, local line networks
Series Q	Switching and signalling
Series R	Telegraph transmission
Series S	Telegraph services terminal equipment
Series T	Terminals for telematic services
Series U	Telegraph switching
Series V	Data communication over the telephone network
Series X	Data networks, open system communications and security
Series Y	Global information infrastructure, Internet protocol aspects and next-generation networks
Series Z	Languages and general software aspects for telecommunication systems